



TECHNICAL SPECIFICATION



**Conductors for overhead lines – Fiber reinforced composite core used as supporting member material –
Part 1: Polymeric matrix composite cores**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.240.20

ISBN 978-2-8322-6983-1

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	8
4 Symbols and abbreviated terms.....	10
5 Requirements	10
5.1 Composite core manufacturing.....	10
5.2 Composite core sampling and tests.....	10
5.2.1 General	10
5.2.2 Type tests.....	11
5.2.3 Sample tests.....	11
5.2.4 Routine tests	11
5.3 Composite core traceability and packaging	11
6 Composite core thermal performance	11
6.1 General.....	11
6.2 Maximum continuous temperature of the composite core: $T_{C,CORE}$	12
6.3 Temperature limit for use in peak load of the composite core: $T_{P,CORE}$	12
7 Tests for the composite core characterization.....	12
7.1 Appearance	12
7.2 Diameter.....	12
7.2.1 Diameter measurement for single wire composite core	12
7.2.2 Diameter measurement for multi-wires composite core	13
7.3 Lay length measurement for multi-wires composite core	14
7.4 Protective layer thickness	15
7.5 DC electrical resistance	15
7.6 Mass per unit length	15
7.7 Tensile test.....	15
7.8 Bending test.....	16
7.8.1 General	16
7.8.2 Mandrel test	16
7.8.3 Coiling test	17
7.9 Measurement of Glass transition temperature (by DMA).....	18
7.10 Coefficient of thermal expansion	19
7.10.1 Sample preparation	19
7.10.2 Procedure.....	19
7.11 T_{onset} Thermolysis determination.....	20
7.12 Isothermal ageing	21
7.12.1 General	21
7.12.2 Product stability at $T_{C,CORE}$	21
7.12.3 Product stability at $T_{P,CORE}$	22
8 Optional tests	22
8.1 Twisting test	22
8.2 Crushing test	23
8.3 Salt fog test	24

8.4	Fiber volume ratio	24
8.4.1	General	24
8.4.2	TGA method	24
8.4.3	Calculated method	26
8.5	Porosity	26
8.6	UV ageing	27
Annex A (normative)	Testing table	28
Annex B (normative)	Arrhenius thermal ageing test.....	29
B.1	General.....	29
B.2	Ageing temperatures, number of samples and picking frequency	29
B.2.1	Overview	29
B.2.2	Definition of the testing plan	29
B.3	Test method.....	30
Annex C (informative)	For more info on composite core T_g	34
Bibliography	35
Figure 1	– Measurement of multi-wire core diameter	13
Figure 2	– Illustration of the mandrel test	17
Figure 3	– Illustration of the coiling test	18
Figure 4	– CTE test setup	19
Figure 5	– Illustration for T_{onset} thermolysis determination.....	20
Figure 6	– Illustration of the twisting test.....	23
Figure 7	– Illustration of the crushing test	24
Figure 8	– TGA curve for the measurement of weight loss versus temperature	25
Figure B.1	– Example of decay curves	31
Figure B.2	– Example of decay curves and identification of times to end-point according to method A	31
Figure B.3	– Example of decay curves and identification of times to end-point according to method B	32
Figure B.4	– Example of Arrhenius curve with the long-term extrapolation to 40 years	32
Figure C.1	– Example of storage modulus and loss modulus curves and T_g point determination.....	34
Table 1	– Testing table for core diameter measurement by core type.....	14
Table 2	– DMA testing specification	18
Table A.1	– Tests on composite core	28

INTERNATIONAL ELECTROTECHNICAL COMMISSION

CONDUCTORS FOR OVERHEAD LINES – FIBER REINFORCED COMPOSITE CORE USED AS SUPPORTING MEMBER MATERIAL –

Part 1: Polymeric matrix composite cores

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

IEC TS 62818-1 has been prepared by IEC technical committee 7: OVERHEAD ELECTRICAL CONDUCTORS. It is a Technical Specification.

The text of this Technical Specification is based on the following documents:

Draft	Report on voting
7/752/DTS	7/754/RVDTS

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this Technical Specification is English.

A list of all parts in the IEC 62818 series, published under the general title *Conductors for overhead lines – Fiber reinforced composite core used as supporting member material*, can be found on the IEC website.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

The first conductors using a composite core were installed in the early 2000s. Since then, they have been increasingly used by utilities worldwide. As a result, there is a need for an IEC publication to agree on tests methods to qualify these cores.

Because of the variety of products used for this purpose, this document does not set minima or maxima (usually provided by the manufacturer), but rather standardizes testing methods to ascertain the numerical values of the basic properties needed by the purchaser to choose the right supporting member material according to the properties of the overhead lines conductors. Future discussion items for review may include performance level and acceptance criteria, other ageing tests and criteria or other relevant tests.

In a future document, tests on the complete conductor which include the composite core will be covered in detail (for example salt fog, corrosion test, mechanical tests, thermal tests, flexural under tension, etc.).

CONDUCTORS FOR OVERHEAD LINES – FIBER REINFORCED COMPOSITE CORE USED AS SUPPORTING MEMBER MATERIAL –

Part 1: Polymeric matrix composite cores

1 Scope

This part of IEC 62818, which is a Technical Specification, establishes a system of fiber reinforced composite core used as supporting member material in conductors for overhead lines which may be used as the basis for specifications. This document is applicable to fiber reinforced composite core, with polymeric matrix, used as supporting member material in conductors for overhead lines.

This document gives guidance on:

- defining the common terms used for fiber reinforced composite core with polymeric matrix,
- prescribing common methods and recommendations to characterize the properties of fiber reinforced composite core based on single or multi-wires with PMC (Polymeric Matrix Composite) used as supporting member material in conductors,
- prescribing or recommending acceptance or failure criteria when applicable.

These tests, criteria and recommendations are intended to ensure a satisfactory use and quality under normal operating and environmental conditions.

This document does not apply to compliance criteria which may be required but indicative values could be given in Annexes for guidance.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60068-2-11:2021, *Environmental testing – Part 2-11: Tests – Test Ka: Salt mist*

IEC 60216-1:2013, *Electrical insulating materials – Thermal endurance properties – Part 1: Ageing procedures and evaluation of test results*

IEC 60468:1974, *Method of measurement of resistivity of metallic materials*

ISO 527-5:2021, *Plastics: Determination of tensile properties – Part 5: Test conditions for unidirectional fiber-reinforced plastic composites*

ISO 4892-2:2013, *Plastics: Methods of exposure to laboratory light sources – Part 2: Xenon-arc lamps*

ISO 11358-1:2022, *Plastics – Thermogravimetry (TG) of polymers – Part 1: General principles*